

35101400 AGGREGATE BASE COURSE, TYPE B (LCDOT)

Effective: December 14, 2012

Revised: April 10, 2017

Description: This work shall consist of furnishing and placing aggregate base course material on a prepared subgrade or subbase.

Materials: The aggregate shall meet the requirements of Article 1004.04 of the "Standard Specifications" except that:

The aggregate material shall be limited to crushed gravel, crushed stone, crushed concrete or RAP.

The RAP shall be well graded from coarse to fine. RAP that is gap-graded or single-sized will not be accepted.

The plasticity index requirements will be waived.

General: The work shall be performed according to Section 351 of the "Standard Specifications".

Method of Measurement: Aggregate Base Course, Type B will be measured for payment in tons according to Article 311.08(b) of the "Standard Specifications". The following excess moisture content correction will apply to Aggregate Base Course, Type B:

When the unit of measurement for the aggregate is tons, the aggregate may be weighed in trucks or freight cars. The Contractor shall furnish or arrange for the use of scales of a type approved by the Engineer. If, at the time the Type B aggregate is weighed, it contains more than six percent of absorbed and free moisture by weight, a deduction for the amount of moisture in excess of this amount will be made in determining the pay quantity. Any aggregate that has been stockpiled will be weighed at the time it is incorporated into the work.

Basis of Payment: This work will be paid for at the contract unit price per ton for AGGREGATE BASE COURSE, TYPE B. *The unit price shall include all equipment, materials and labor required to furnish, weigh and place the base course.*