

LC400151 HOT-MIX ASPHALT SURFACE ADJUSTMENT AT MANHOLES

(LCDOT) For use on LCDOT let projects only - do not include in IDOT let projects.
Delete this note from the Contract Specifications.

Effective: January 1, 2007

Revised: May 20, 2014

Description: This work shall consist of removing the existing hot-mix asphalt surface from around an existing manhole and placing hot-mix asphalt materials around the manhole frame to protect snow plows from the protruding casting.

Materials: The hot-mix asphalt materials shall meet the requirements of Section 1030 of the "Standard Specifications".

General: *The existing hot-mix asphalt surface shall be saw cut and the pavement removed to a depth of approximately 1½". The removal area shall be primed and Hot-Mix Asphalt Surface Course, Mix "D", N50, shall be placed and compacted according to Section 406 of the "Standard Specifications". The finished surface shall be ¼" above the casting.*

Method of Measurement: Hot-Mix Asphalt Surface Adjustment at Manholes will be measured for payment in place for each manhole location.

Basis of Payment: This work will be paid for at the contract unit price per each for HOT-MIX ASPHALT SURFACE ADJUSTMENT AT MANHOLES. *The unit price shall include all equipment, materials and labor required to adjust the HMA surface at the manhole.*